
SPECIFICATION		
		FANSO
Electrical characteristics (Typical values relative to cells stored for six months at +30 °	C max)	ER14250S 3.6
● Nominal capacity Discharged capacity at 10mA,150 °C centigrade to end voltage of 2.5V	600mAh	Key features
		<ul> <li>High and stable operating voltage</li> </ul>
<ul> <li>Open circuit voltage</li> </ul>	3. 65V	Long shelf life ● Anual self-discharge rate lower than 2% at +25℃
		Long operating life
Max. recommended continuous current	50mA	<ul> <li>High energy density (700wh/kg)</li> <li>Wide operating temperature rang</li> </ul>
		<ul> <li>Stainless steel can and cover</li> </ul>
	100 1	Hermetic glass-to-metal sealing
Max. Pulse capability 100mA,0.1 second pulses every 2 minutes, drained with 50%, 10mA at 150 °C from 100mA,0.1 second pulses every 2 minutes, drained with 50%, 10mA at 150 °C from	100mA	Non-flammable electrolyte
undischarged cells with 20µA base current, yield voltage readings above 2.7V, the value may vary according to the pulse characteristics, the temperature and	111	Compliant with IEC 86-4 safety standard
the cell's previous history		<ul> <li>Non-restricted for transport</li> </ul>
Operating temperature rang	20 ℃~+150 ℃	Main applications
		<ul> <li>Exploration Measurement Instrumen (mills,oil,fields)</li> </ul>
o Weight	10g	Data Recording Instrument
		Military Communication Equipment
<ul> <li>Diameter(max)</li> </ul>	14.65mm	Electronic Testing Equipment
		<ul> <li>Navigation And Aviation Equipment</li> </ul>


25.2mm



3.6V



## Capacity vs Temperature curve(cut off with 2.0V)



## STORAGE:

Height(max)

Stored in clean, dry and cool circumstances (the temperature should be 20 degress or lower, less than 30 degress)

## WARNING

Don't charge, crush, disassemble, expose contents to water, heat above 160°C or may lead to explosion , burn or poison goods leakage Discarded battery should be buried deeply to the ground .

Information in the document is just for reference, not for gurantee of battery performance, the quality of battery is subject to the buyer and seller's final comfirmation in the contract.