

Anti-static Coating Sheet Technical Data Sheet

Product Structure



Technical Data

Project	Test method	Result
Transmissivity	Over 90%	91.5
Haze	Under 1%	0.2
Pencil Hardness	Pencil hardness tester	Over 5H
Surface resistance	Surface resistance machine	$10^6 \sim 10^8 \Omega/\text{cm}^2$
R.C.A Test	175g, 50-200 rounds	Pass
Adhesion	Cross cut test	100/100
Thermal shock test	-40°C/45min, 85°C/85min, 27 rounds	Pass
Heat and humidity test	85°C, 85RH, 72 hours	Pass
Salt tolerance	35°C, 5%, Sodium chloride water, 48 hours	Pass
Chemical resistance	alcohol 500g, 250 rounds	Pass

Test Material: 5mm Clear Acrylic Sheet

