

GENERAL FEATURES

- Environmentally friendly
- Thick plate with high Tin low Calcium alloy
- High Reliability and Good Quality
- Deep Discharge Recovery
- High Power Density
- Long Service Life, in Float or Cyclic


APPLICATIONS

- Solar & Wind energy system
- Cable TV Systems
- Telecom systems
- Wheel chair & Golf Car
- Marine Equipment
- Railway Systems
- Emergency Power System



DIMENSIONS & WEIGHT

Length(mm)	260±1
Width(mm)	180±1
Height (mm)	265±1
Total Height(mm)	272±1
Weight(kg)	34.5±3%



COMPLIED STANDARDS

IEC 60896-21/22	JIS C8704
YD/T799	BS6290 part4
GB/T 19638	UL 1989

TECHNICAL SPECIFICATIONS



Nominal Voltage		6V(3 cells per unit)
Design Floating Life @ 25°C		12 Years
Nominal Capacity @25 °C(20 hour rate @12.50A,5.25V)		250Ah
Capacity @25°C	10 hour rate (22.75A,5.40V)	227.5Ah
	5 hour rate (39.80A,5.25V)	199.0Ah
	1 hour rate (139.0A,4.80V)	139.0Ah
Internal Resistance	Full Charged Battery@25 °C	≤2.5mΩ
Ambient Temperature	Discharge	-20°C~50°C
	Charge	-20°C~50°C
	Storage	-20°C~50°C
Max.Discharge Current @25°C		2000A(5s)
Capacity affected by Temperature (10 hr Capacity)	40°C	102%
	25°C	100%
	0°C	85%
	-15°C	65%
Self-Discharge@25 °C per Month		3%
Charge (Constant Voltage) @25 °C	Standby Use	Initial Charging Current Less than 45.0A Voltage 6.8-6.9V
	Cycle Use	Initial Charging Current Less than 45.0A Voltage 7.2-7.45V

BATTERY DISCHARGE TABLE

Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	321.8	205.5	151.0	139.0	88.3	62.0	42.0	27.8	24.75	13.25	3.00
1.67V	316.0	201.8	148.3	136.3	86.5	60.8	41.3	27.3	24.25	13.00	2.95
1.70V	310.0	198.0	145.5	133.8	85.0	59.8	40.5	26.8	23.75	12.75	2.88
1.75V	304.3	194.3	142.8	131.3	83.3	58.5	39.8	26.3	23.50	12.50	2.83
1.80V	292.5	186.8	137.3	126.3	80.0	56.3	38.3	25.3	22.75	12.38	2.78

Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	619.3	395.5	290.8	266.8	169.5	119.0	81.0	53.3	47.8	25.9	5.78
1.67V	608.0	388.3	285.3	262.0	166.5	117.0	79.5	52.5	46.8	25.3	5.65
1.70V	596.8	381.0	280.0	257.0	163.5	114.8	78.0	51.5	46.0	25.1	5.55
1.75V	585.5	373.8	274.8	252.3	160.3	112.5	76.5	50.5	45.0	24.8	5.45
1.80V	563.0	359.5	264.3	242.5	154.3	108.3	73.8	48.5	43.3	24.0	5.35

Note The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **CBB** for the latest information.

PERFORMANCE CHARACTERISTICS



BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0 optional)	Flame Si-Rubber aging resister	Female Copper Insert M8 (torque: 7~9N.m)	Advanced AGM separator for high pressure cell design	Dilute high purity sulphuric acid	Two layers epoxy resin seal

CBB Battery Technology Co., Ltd.

RM504,55 Hanxing Zhong Road, Zhongcun, Panyu, Guangzhou 511495 China

Tel: +86-020-84888946 Fax: +86-020-62824569

Copyright©2022 CBB Battery Technology Co., Ltd.

Koyama®

www.cbb-battery.com