

## GENERAL FEATURES

- Environmentally friendly
- Thick plate with high Tin low Calcium alloy
- High Reliability and Good Quality
- Deep Discharge Recovery
- High Power Density
- Long Service Life, in Float or Cyclic



## APPLICATIONS

- Solar & Wind energy system
- Cable TV Systems
- Telecom systems
- Wheel chair & Golf Car
- Marine Equipment
- Railway Systems
- Emergency Power System



## DIMENSIONS & WEIGHT

Length(mm)	229±1
Width(mm)	138±1
Height(mm)	208±1
Total Height(mm)	212±1
Weight(kg)	17.5±3%



## COMPLIED STANDARDS

IEC 60896-21/22	JIS C8704
YD/T799	BS6290 part4
GB/T 19638	UL 1989

## TECHNICAL SPECIFICATIONS



Nominal Voltage		12V(6 cells per unit)
Design Floating Life @25°C		12 Years
Nominal Capacity @25°C (20 hour rate@2.90A,10.50V)		58Ah
Capacity @25°C	10 hour rate (5.28A,10.8V)	52.8Ah
	5 hour rate (9.2A,10.5V)	46.0Ah
	1 hour rate (32.2A,9.6V)	32.2Ah
Internal Resistance	Full Charged Battery@25°C	≤7.0mΩ
Ambient Temperature	Discharge	-20°C~50°C
	Charge	-20°C~50°C
	Storage	-20°C~50°C
Max.Discharge Current@25°C		580A(5s)
Capacity affected by Temperature (10 hr Capacity)	40°C	102%
	25°C	100%
	0°C	85%
	-15°C	65%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 13.05A Voltage 13.6-13.8V
	Cycle Use	Initial Charging Current Less than 13.05A Voltage 14.4-14.9V

## BATTERY DISCHARGE TABLE

### Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	74.6	47.7	35.0	32.2	20.5	14.4	9.7	6.4	5.74	3.07	0.70
1.67V	73.3	46.8	34.4	31.6	20.1	14.1	9.6	6.3	5.63	3.02	0.68
1.70V	71.9	45.9	33.8	31.0	19.7	13.9	9.4	6.2	5.51	2.96	0.67
1.75V	70.6	45.1	33.1	30.5	19.3	13.6	9.2	6.1	5.45	2.90	0.66
1.80V	67.9	43.3	31.8	29.3	18.6	13.1	8.9	5.9	5.28	2.87	0.64

### Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	143.7	91.8	67.5	61.9	39.3	27.6	18.8	12.4	11.1	6.0	1.34
1.67V	141.1	90.1	66.2	60.8	38.6	27.1	18.4	12.2	10.8	5.9	1.31
1.70V	138.4	88.4	65.0	59.6	37.9	26.6	18.1	11.9	10.7	5.8	1.29
1.75V	135.8	86.7	63.7	58.5	37.2	26.1	17.7	11.7	10.4	5.7	1.26
1.80V	130.6	83.4	61.3	56.3	35.8	25.1	17.1	11.3	10.0	5.6	1.24

**Note** The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **CBB** for the latest information.

#### PERFORMANCE CHARACTERISTICS



#### BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0 optional)	Flame Si-Rubbeand aging resistanacer	Female Copper Insert M6(torque:4 ~6N.m)	Advanced AGM separator for high pressure cell design	Dilute high purity sulphuric acid	Two layers epoxy resin seal