

## Technical Data For PVC Super Clear Film

Item	Date	
Thickness Tolerance      %	±5	
Width Tolerance          mm	±2	
Combining Fastness of aluminum layer      Ω / □		
Even degree of aluminum layer      %		
Corona Treatment          Dyne	> 38	
Wetting tensile              mN/m	≥38	
Heat shrinkage          %	MD	15—20
	TD	0—3
Tensile strength          Mpa	MD	≥90
	TD	≥60
Tear strength (right angle)    N	MD	≥3.0
	TD	≥1.7
Oxygen permeance      cm <sup>3</sup> /(m <sup>2</sup> · 24h · 0.1Mpa)	≤3.0	
Vapor permeance          g/(m <sup>2</sup> · 24h)	≤4.0	
features	It has good tensile strength and , high brighrness, no static, suit for printing &lamination	
Usage	Applied for food wrapping,industrial usage.	